

TWE-711M

AWS A5.20 E71T-1M
EN ISO 17632-A-T 46 3 P M21 1 H10
JIS Z 3313 T 49J 0 T1-1 M A-U

Characteristics and Applications:

TWE-711M is a flux-cored wire designed to be used with Ar/ CO₂ gas. It's available for all-position welding with both single and multiple pass welds on mild and 490N/mm² high tensile steels. It features good impact properties, less fume, stable arc, easy slag removable and excellent X-Ray inspection. Typical applications include shipbuilding, storage vessels, structural fabrication, machinery and piping etc.

Notes on usage:

1. Use DC(+) polarity.
2. Use 75~80%Ar + 25~20%CO₂ as shielding gas.
3. Keep the product dry, while it is stored or delivered.


Typical chemical composition of weld metal (wt%) :

	C	Mn	Si	P	S
AWS	≤0.12	≤1.75	≤0.90	≤0.03	≤0.03
EN ISO	-	≤2.0	-	-	-
Typical value	0.04	1.30	0.30	0.013	0.007

Typical mechanical properties of weld metal :

	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-1bf) -30°C (-20°F)
AWS	≥390(58)	490-670(70-95)	≥22	≥27(20)
EN ISO	≥460(67)	530-680(77-99)	≥20	≥47(35)
Typical value	567(82)	608(88)	29	66(49)

Welding position:



Sizes and recommended parameter range (DC < + >):

Stick out: 15-25 (mm), flow rate: 20-25 (l/min)

Position	Diameter (mm)	1.2
F, HF		140A~300A / 22V~34V
H		140A~280A / 22V~32V
VU, OH		140A~220A / 22V~26V
VD		230A~280A / 28V~32V

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.