

# TS-2209LB

相當規格：

AWS A5.4 E2209-15

EN ISO 3581-A-E22 9 3 N L B 4 2

JIS Z 3221 ES2209-15

## 特性與用途：

TS-2209LB 為特殊鹼性焊劑，可提供全位置焊接、脫渣性優，專為焊接雙相不銹鋼鋼管而設計。其組織是沃斯田鐵及肥粒鐵雙重結構組織，具有較高降伏強度及在氯化物溶液有較佳的抗應力腐蝕龜裂（SCC）和良好的耐孔蝕，最適合鋸接含22%Cr的雙相不銹鋼，諸如UNS S31803(即Alloy2205)等。可應用在熱交換器管件、輸油管、鑽油平台、氣井、管線管（Line piping）等。

## 注意事項：

- (1)母材表面之油污、灰塵及雜物等須確實除淨。
- (2)鋸縫之清理應使用不銹鋼刷清除，以免鐵屑混入鋸道金屬中影響鋸道品質。
- (3)若須以織動方式施鋸時，其織動的寬度應在鋸條直徑的2.5倍以內。
- (4)使用前鋸條須於250~300°C乾燥60分鐘，使用時取出少量放入保溫100°C~150°C之乾燥筒內，攜出鋸條量最多以4小時量為宜。
- (5)儘可能使用較低之鋸接電流且壓低電弧長度，以使母材稀釋減少防止龜裂，以免影響鋸道金屬的沃斯田鐵-肥粒鐵相平衡。

## 鋸道化學成份之一例(wt%)：

	C	Mn	Si	P	S	N	Cr	Ni	Mo	Cu	抗孔蝕 當量
AWS	≤0.04	0.5-2.0	≤1.00	≤0.04	≤0.03	0.08-0.20	21.5-23.5	8.5-10.5	2.5-3.5	≤0.75	-
EN ISO	≤0.04	0.5-2.0	≤1.00	≤0.04	≤0.03	0.08-0.20	21.5-23.5	7.5-10.5	2.5-3.5	≤0.75	-
例值	0.035	0.70	0.35	0.03	0.008	0.160	22.75	9.67	3.1	0.07	35.5

## 鋸道機械性質之一例：

	抗拉強度 MPa(ksi)	伸長率 %	衝擊值 J (ft-lbf)	
			-20°C(0°F)	-50°C(-60°F)
AWS Spec	≥690(100)	≥20	-	-
EN ISO Spec	≥690(100)	≥15	-	-
例值	865(125)	34	70(52)	54(40)

## 鋸接位置：



## 適用電流範圍：(AC或DC+)

直徑及長度(mm)	2.6x300	3.2x350	4.0x350	4.8x350
電流範圍 (Amps)	平 鋸 60-90	80-110	130-170	180-210
	立仰鋸 50-70	70-110	100-130	-

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.