

TFW-309LT

相當規格：

AWS A5.22 E309LT0-1
EN ISO 17633-A-T 23 12 L R C1 3
JIS Z 3323 TS309L-F C 0

特性與用途：

因鋸道金屬為沃斯田鐵組織中含有適量的肥粒鐵，所以鋸接性、鋸道完整性及耐龜裂性優。此產品為平鋸、角鋸專用鋸線，常使用於異種母材低合金鋼、耐熱鋼、耐蝕鋼及覆面鋼底道覆層之鋸接。

注意事項：

- (1) 使用之CO₂保護氣體純度須在99.8%以上。
- (2) 施鋸場所需有良好之遮風屏蔽，以防保護氣體飛散而產生鋸接缺陷。
- (3) 鋸接處之油污、水份等須清除乾淨。
- (4) 運送和儲存時要注意防潮。

鋸道化學成份之一例(wt%)：

	C	Mn	Si	P	S	Cr	Ni
AWS	≤ 0.04	0.5-2.5	≤ 1.0	≤ 0.04	≤ 0.03	22.0-25.0	12.0-14.0
EN ISO	≤ 0.04	≤ 2.5	≤ 1.2	≤ 0.030	≤ 0.025	22.0-25.0	11.0-14.0
例值	0.024	1.62	0.62	0.022	0.009	24.07	12.33

鋸道機械性質之一例：

	抗拉強度 MPa(ksi)	伸長率 %
AWS	≥520(75)	≥30
EN ISO	≥510(74)	≥25
例值	580(84)	34

鋸接位置：



鋸接參數建議：(DC+)

伸出長度：15-20(mm)、氣體流量：20-25 (l/min)

鋸接位置	線徑(mm)	1.2	1.6
平鋸(F) 、水平角鋸(HF)		150A-240A / 25V-32V	180A-300A / 27V-35V

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.



天泰鋸材
AN ILLINOIS TOOL WORKS COMPANY

台灣 · 台南市仁德區保安里開發四路六號
TEL:886-6-2663721 /FAX:886-6-2664301
E-mail:tworder@itwweld.com
http://www.tientai.com

綠鋸
藥包